

Viral Filtration Efficiency (VFE) in ASTM F2101

Proven that OOH SHIELD technology can effectively **filter virus (>99.9a%)**



Sponsor:
Eddie Yam
Intertek Testing Services Hong Kong Ltd.
1/F, Garment Centre, 576 Castle Peak Road
Kowloon,
HONG KONG

Viral Filtration Efficiency (VFE) Final Report

Test Article: modified non-woven
colour: White
Style #1001
Study Number: 1280865-S01
Study Received Date: 25 Mar 2020
Testing Facility: Nelson Laboratories, LLC
6280 S. Redwood Rd.
Salt Lake City, UT 84123 U.S.A.
Test Procedure(s): Standard Test Protocol (STP) Number: STP0007 Rev 16
Deviation(s): None

Summary: The VFE test is performed to determine the filtration efficiency of test articles by comparing the viral control counts upstream of the test article to the counts downstream. A suspension of bacteriophage Φ X174 was aerosolized using a nebulizer and delivered to the test article at a constant flow rate and fixed air pressure. The challenge delivery was maintained at $1.1 - 3.3 \times 10^3$ plaque forming units (PFU) with a mean particle size (MPS) of $3.0 \mu\text{m} \pm 0.3 \mu\text{m}$. The aerosol droplets were drawn through a six-stage, viable particle, Andersen sampler for collection. The VFE test procedure was adapted from ASTM F2101.

All test method acceptance criteria were met. Testing was performed in compliance with US FDA good manufacturing practice (GMP) regulations 21 CFR Parts 210, 211 and 820.

Test Side: Either
Test Area: $\sim 40 \text{ cm}^2$
VFE Flow Rate: 28.3 Liters per minute (L/min)
Conditioning Parameters: $85 \pm 5\%$ relative humidity (RH) and $21 \pm 5^\circ\text{C}$ for a minimum of 4 hours
Positive Control Average: 1.6×10^3 PFU
Negative Monitor Count: < 1 PFU
MPS: $2.9 \mu\text{m}$

Study Director

James W. Luskin

Study Completion Date



1280865-S01

801-290-7500 | nelsonlabs.com | sales@nelsonlabs.com

myf

FRTD007-0001 Rev 16

Page 1 of 2

Results:

Test Article Number	Percent VFE (%)
1	>99.9 ^a
2	>99.9 ^a
3	>99.9 ^a
4	>99.9 ^a
5	>99.9 ^a

^a There were no detected plaques on any of the Andersen sampler plates for this test article.

The filtration efficiency percentages were calculated using the following equation:

$$\% VFE = \frac{C - T}{C} \times 100$$

C = Positive control average

T = Plate count total recovered downstream of the test article

Note: The plate count total is available upon request